



255 Wooster Road North • Barberton, Ohio 44203
Phone: (330) 745-9016 • Fax: (330) 745-4886
www.tahomarubberplastics.com

30T BUFFINGS
(40 Mesh Ground Rubber)
CODE: P-2035

SPECIFICATION SHEET

MATERIAL:

GROUND RUBBER BUFFINGS

Typical Chemistry

Rubber Hydrocarbon (RHC)	45% Minimum
Carbon Black	35% Maximum
Acetone Extract	19% Maximum
Ash Content	8% Maximum

DESCRIPTION:

A UNIFORM MIXTURE OF SBR/NR 100% FROM TREAD STOCK

Typical Screen Distribution:

RETAINED ON 20 MESH	0 - Nil
RETAINED ON 30 MESH	0 - 2%
RETAINED ON 35 MESH	10 - 20%

SPECIFIC GRAVITY: 1.14 → 1.18

MOISTURE: 1.0% MAX

The Technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. Buyer assumes all risks of use, storage and handling of product. **No warranty, express or implied, is made including, but not limited to, implied warranties of merchantability and fitness for a particular purpose.** Nothing contained herein shall be construed as a license to operate under, or recommended to infringe, any patents.