



255 Wooster Road North • Barberton, Ohio 44203  
Phone: (330) 745-9016 • Fax: (330) 745-4886  
www.tahomarubberplastics.com

## **PRODUCTIVE RUBBER COMPOUND P-1066 REFINED SHEETED COMPOUND**

### **Typical Properties**

Density:	1.16 ± .04 gms/cm
Shore A Durometer:	60 ± 6
Tensile Strength PSI	2200 Minimum
Elongation	300% Minimum
Contamination:	Free of Lumps, Metal or Pre-Scorch
Form:	Un-vulcanized Sheeted, Wig Wag, Cut or Pre-Weigh to Order. Does not contain sulfur or accelerators.
Packaging:	Standard Skid (1500 - 2000# Typical)

### **Typical Composition**

SBR/NR:	100
Carbon Black:	50
Chemicals, Oil/Other	30

### **Material Source**

Basic Material is Commercial Productive Tire Tread Compound *or Similar*.

### **Typical Applications**

Molded Sheets or Parts. Compound loading (extension) for cost reduction

### **Samples**

Available upon request

### **Availability**

Typically stocked in Barberton, OH and or Abbeville, SC ready to ship in 2-4 days.

The Technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. Buyer assumes all risks of use, storage and handling of product. **No warranty, express or implied, is made including, but not limited to, implied warranties of merchantability and fitness for a particular purpose.** Nothing contained herein shall be construed as a license to operate under, or recommended to infringe, any patents.